SYNOCURE 9237 S 70

Hydroxyl Functional Acrylic, 3.1% OH

Product Information	SYNOCURE 9237 S 70 is a hydroxyl functional acrylic resin designed to crosslink at room temperature with polyisocyanates.			
	SYNOCURE 9237 S 70 is particularly well suited for use in high quality compliant industrial coatings, marine coatings, heavy duty and protective coatings such as structural steelwork.			
	Outstanding properties of this acrylic resin are:			
	 Excellent chemical and stain resistance Economy in use Good durability Excellent adhesion 			
Sales Specification	Non-volatile content at 125°C, % (ISO 3251)	69 – 71		
	Viscosity at 25°C, mPa.s (ISO 3219)	2,000 – 3,000		
	Colour, Gardner scale (ISO 4630)	Max. 2		
	Acid value, mg KOH/g (ISO 2114)	Max. 10		
Other Properties	Volatile	Solvesso 100 / Xylene		
	Density at 20°C, g/cm ³ (ISO 2811)	0.99		
	Hydroxyl Content, %	3.1		
	Hydroxyl Equivalent Weight (on resin solid)	550		
	Noted: Acid value & hydroxyl content quoted relative to solid resin			
Recommendations for Use	SYNOCURE 9237 S 70 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.			
	SYNOCURE 9237 S 70 reacted with Tolonate HDT-LV2 ⁽¹⁾ in stoichiometric proportions has a usable pot life in excess of a full working day at normal room temperatures. The use of catalysts or higher temperatures will reduce this storage period.			



The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

	Hydroxyl equivalent weight	t = <u>17 X 100</u> %OH		
	Isocyanate equivalent weig	ht = <u>42 X 100</u> %NCO		
	Using Tolonate HDT-LV2 ⁽¹⁾ , the recommended ratios would be:			
		on solid resin	as supplied	
	SYNOCURE 9237 S 70 Tolonate HDT-LV2 ⁽¹⁾	550 182	786 182	
	<u>SOLUBILITY</u>			
	The solvents chosen for paints and lacquers based on SYNOCURE 9237 S 70 should be free of water and should not contain groups which react with isocyanates.			
	Esters and ketones are true solvents for this type of system and are usually used with aromatic hydrocarbon diluents.			
	Notes: (1) Perstorp			
Precautions for Use	Please refer to corresponding Safety Data Sheet.			
Storage Recommendations	SYNOCURE 9237 S 70 should be stored indoors in the original containers in a dry place at temperature between 5°C and 30°C. Avoid exposure to direct sunlight or frost.			
Shelf Life	Under the above mentioned storage conditions the shelf life of the resin will be 12 months.			



The world is our inspiration Arkema Coating Resins Malaysia Sdn Bhd PLO 491, Jalan Keluli, Pasir Gudang Industrial Estate, 81700 Pasir Gudang, Johor, Malaysia

Telephone: (60) 7-253 6688 Fax: (60) 7-251 8453

Visit our website: www.arkemacoatingresins.com IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

© Arkema Inc. All rights reserved. SYNOCURE® is a trademark of Arkema Inc. Version: 01 / December 2011